

April 15, 1928

CORROSION RESISTANCE OF IRON AND STEEL

The Letter Circulars are designed to answer specific inquiries and at the same time to obviate the necessity for preparation of a large number of letters on the same subject. There is no guarantee that the information given in the Letter Circulars is correct except as of the date of issue. Material of a permanent value appears in the printed publications of the Bureau.

Letter Circulars are not available in the Government Printing Office, and the supply at the Bureau of Standards is limited.

Many inquiries are received by this Bureau in regard to the resistance to corrosion of cast iron, and of steel, wrought iron, commercially pure open-hearth iron and copper-bearing iron or steel in sheet, pipe, wire and other forms both bare and zinc coated or otherwise "rust proofed".

Some inquirers request opinions on the suitability of specific makes or brands of these materials for specific uses.

It is not the policy of the Bureau to recommend or decri specific makes or brands of any article. Its tests and investigations deal with types of material, not with the merits or demerits of a particular maker's product. This Letter Circular is prepared to put those making such inquiries on types of material in touch with published data and opinions on the subject.

There are many papers in scientific and technical periodicals on this subject, dealing with the performance of these materials in different types of service. Most of the papers have naturally been written by men on the technical staff of various producers of the materials.

Instances of good or even phenomenal life for many types of material are on record, but since, in general, only one type of material was used in the particular service reported on, the question as to what life competing materials would have given under identical service conditions is unanswered.

Another class of papers are those, again more often written by the technicians of the producers than by users, which report accelerated laboratory tests of various competing materials. The actual data reported are in general presumably accurate. The interpretation thereof is often subject to discussion, sometimes acrimonious, by those whose experience or whose laboratory experiments lead to different conclusions. Some of this criticism is often quite just. For example, two materials completely submerged in an acid may show relative rates of corrosion such that material A is obviously more resistant than material B. But it does not follow that on exposure to salt air, for instance, material A is superior to material B. The correlation of accelerated laboratory tests of different kinds with comparative service tests carried out under identical conditions is very desirable but no conclusive correlation of such a nature has yet been made, and such tests as are in progress must go on for years before the comparative service tests are completed so that valid conclusions may be drawn therefrom.

A third class of papers or reports are those by impartial observers, such as users of the products under discussion or by technical societies whose committees are made up of both users and producers, and among the latter, those interested in the manufacture of the various competing types of material.

Among the accounts of presumably impartial and comprehensive tests is one of work done at the German Materialprüfungsamt and reported by Bauer (Mitt. Mat. 38, 1920, p. 85, Stahl u. Eisen 41, 1921, pp. 37, 76). Exposure tests, lasting 4 to 4-1/2 years were made in a relatively pure atmosphere at the laboratory, in one contaminated by industrial smoke at a steel works, and in salt air, of several series of steels in large sheets, not freed from scale, averaging about 0.08% C, 0.45% Mn, 0.10% Ni and varying in copper content from 0.10% to 0.40%. No copper-free material was tested. Other large sheets were immersed in sea-water for 14 months, and still others were buried in the ground for 5 years at the same three locations as were chosen for atmospheric tests.

Other exposure tests and many laboratory tests in various corroding media were made on smaller specimens of the materials, freed from scale. Bauer states that in the industrial atmosphere of the steel works, where sulphurous or sulphuric acid was doubtless present, the copper-rich sheets were decidedly less attacked than those lower in copper. Under all the other conditions of exposure or test Bauer was

unable to find any consistent differences in behavior that would warrant his accepting the idea that a variation in copper content from 0.10% to 0.40% had any clear effect upon the life of the sheets.

While these German government tests covered quite a range of conditions and quite a period of time, they were not as exhaustive nor as long continued as some American tests, nor did they include several types of iron and steel much used in the United States.

The American Society for Testing Materials through its Committee A-5 has conducted a series of exposure tests at Pittsburgh, Annapolis and Fort Sheridan, Ill., upon bare (un-galvanized) sheets of different gages together with some corrosion tests in Washington, D. C. city water constantly renewed; in acid mine water of the Pittsburgh district, and in brackish water in the Severn River at Annapolis. Both the atmospheric and the underwater tests were made on various ferrous materials, such as wrought iron, commercially pure open-hearth iron, open hearth steel, Bessemer steel etc. low in copper and similar materials with 0.15 to 0.50% copper.

The results of the inspection of these tests are given in detail, by tables and photographs, in the Proceedings of the American Society for Testing Materials from 1918 on, (which can be consulted at many public libraries or purchased from the Secretary of the Society, 1315 Spruce St., Philadelphia).

In general, the attitude of the committee has been to present the data in progress reports and require the reader to draw his own conclusions. A few tentative conclusions have, however, been drawn. In a report of the sub-committee on inspection, unanimously approved by the sub-committee (Proc. A. S. T. M., Vol. 22, Part 1, 1922, p. 170) it is stated "This information continues to bear out the conclusions of the 1921 report that copper-bearing metal in the Pittsburgh location shows marked superiority in rust-resisting properties as compared to non-copper bearing material of the same general composition". This applies to bare, un-galvanized sheets exposed in the air.

In reference to tests of similar materials immersed in tap, brackish, or mine water, the committee states (Proc. A.S. T.M. Vol. 24, Part 1, 1924, p. 220), "The tests thus far do not indicate any outstanding superiority for any one type

of metal, and the presence of copper added to the various types of metal does not increase its resistance to corrosion, when the samples are totally and continually submerged in running water of acid or alkaline reaction.

Results of the most recent inspection, which will be summarized in the 1926 report of Committee A-5, suggest a ^{very} slight difference in favor of the copper-bearing material in ~~some~~ of the under-water tests. The conclusion drawn by many impartial observers of previous under-water tests has been to the effect that if any difference was detectable, it was in the direction of slightly poorer service under-water from the copper-bearing material. Before final conclusions can be drawn the A. S. T. M. tests will have to be carried to completion.

That final conclusions have not yet been drawn by the A. S. T. M. or by government departments is evidenced by A. S. T. M. Tentative Specifications for hot-dipped galvanized sheets A93-24T (Proc. A. S. T. M. Vol. 24, Pt. 1, 1924, p. 775) and by Standard Specifications for (zinc-coated) corrugated metal pipe culverts (American Association of State Highway Officials and Department of Agriculture) U. S. Department of Agriculture Circular 331, November, 1925, both of which allow the purchase of either copper-bearing or non-copper bearing material.

Since the tests mentioned above are all on bare, ungalvanized material, which is less commonly used in service where corrosion is to be resisted, than is material galvanized or zinc-coated by various methods, it is not yet known by impartial tests what the performance of the various base materials covered with a zinc coating will be. Since the nature of the initial coat of rust or corrosion products that forms upon a piece of iron or steel may affect the progress of the rusting or corrosion it is conceivable that the initial coat may not be similar to that formed on the uncoated sheets used in the atmospheric and submerged corrosion tests.

However, this Committee (A-5) of the American Society for Testing Materials has in progress another comprehensive series of exposure tests on zinc-coated materials with different weights of coating on different base materials, in form of sheets, wire, fencing, etc., coated by different processes.

Exposure tests are to be made at five different locations. Accelerated laboratory tests will be made, for comparison with the exposure tests when the latter are completed. Details of the test program appear in the 1925 Proceedings of the A. S. T. M. Part 1, p. 105.

It is not to be expected that conclusive results of these tests will be obtained for many years. The tests of uncoated material have gone on since about January 1, 1917 and are still incomplete. On account of the much longer life of zinc-coated materials, which will be very marked in the case of the heavier coatings, it is unlikely that even tentative conclusions can be drawn within ten years.

It is rather well-established that within the limit set by the cracking or flaking of the coating on material that has to be formed after galvanizing or zinc-coating, the life of the coating is, broadly, the greater the heavier the zinc coating. The effect of differences in technique or method of zinc coating and of the composition or purity of the coating will in general be secondary to the main factor of the thickness of the coating. It is obvious also that for any given composition, the thicker the sheet, wire, etc. (i.e., the heavier the gage) the longer the life will be. Coating a fabricated article such as garbage cans or wire fencing after fabrication allows the use of a heavier coating than would resist cracking during fabrication and, if heavier coatings are actually used, coating after fabrication is generally believed to produce a superior article.

The Bureau of Standards is cooperating with the A. S. T. M. in the tests on bare and on coated iron and steel and has not completed nor has it under way, separate exposure or service tests in these fields.

The corrosion of pipe in soils is, however, the subject of a separate investigation which has been under way at the Bureau of Standards since 1922. A preliminary report was presented before the American Foundrymen's Association in 1924, (Logan, K. H., Soil Corrosion Investigation, Trans. A. F. A. Vol. 32, 1925, p. 144). Specimens are dug up and inspected every two years. The preliminary report states "In so far as the conclusion may be warranted from short time tests, the results indicate that no one of the commonly used pipe materials tested is generally superior to the others under all soil conditions. On the other hand, the tests seem to show that the pipe material best suited to one soil condition may give a relatively poor showing under a different soil condition".

These tests include wrought iron, commercially pure open-hearth iron, cast iron, open hearth steel, bessemer steel and copper-bearing steel as well as a large number of other materials and various coated specimens. The second inspection is being made in 1926 and a further progress report will be made when the inspection is complete and the results tabulated.

Few comprehensive reports of tests by experimenters unconnected with producers are known in the field of corrosion of water pipes or of culverts, though various producers have made or have under way tests in these important fields.

The U. S. Department of Agriculture, Bureau of Public Roads, installed a few bare and galvanized culverts of bessemer, open-hearth, and copper-bearing steels and of copper bearing iron and ingot iron in Texas in 1915, and reported in its Bulletin 586, February 28, 1918, (which is out of print) on an inspection made after about two years of service. The galvanized culverts were then all in "apparently new condition". The bare culverts were showing some attack but no clear differentiation among the various materials was shown. The Bureau of Public Roads stated in March, 1926 that some difference in condition had recently begun to be shown, and that another inspection is to be made soon, after which, if any worth-while conclusions can be drawn, the results will be promptly published.

The National Research Council, Highway Research Board (Mr. R. W. Crum, Ames, Iowa, Chairman Culvert Committee), is studying the culvert problem but has as yet published no report.

The California Highway Commission, Sacramento, California, has examined some 5000 culverts and is now correlating the information obtained. This will not be completed before June, 1926, at the earliest, and no decision has yet been made as to whether the results will be published.

The Wisconsin Highway Commission, Madison, Wisconsin, is now engaged in a comprehensive field survey of culvert life. Two thousand culverts were inspected, in 1925, but before the work is completed so as to justify giving out information, it is expected that eight thousand will be inspected.

The Sub-Committee, on Corrugated Metal Culverts for Railway Purposes, of the American Railway Engineering Association, states - (Bulletin A. R. E. A. 27, No. 284, Jan. 1923, p.794) "The Sub-committee has no report to make at this time on the question of relative durability".

The conditions of service vary so greatly that it is, so far, impossible accurately to predict the life of any ferrous material in any given service. It is generally equally impossible accurately to predict the relative performance of two different types of material in the same service unless these materials have already been subjected to impartial comparative test under the identical conditions of service.

A common error in the consideration of corrosion tests is to assume that satisfactory or unsatisfactory performance under one set of conditions means that performance will be similar under another set of conditions. The relative standing of different materials is very often altered as the conditions are altered.

For information of practical value, primary dependence must be placed on such experiments as the several A. S. T. M. series of tests and as the culvert inspections under way in various states, in all of which much time must still pass before completion. Isolated service records in which but one material was used only indicate tendencies. Proof of superiority in service requires that the different materials shall have been used under same conditions. Laboratory tests lasting days or months may sometimes be as valuable as service records of years because the variables involved are under control, but many laboratory tests, in the attempt to secure information rapidly, exaggerate the conditions of corrosion and may so alter the conditions as to give misinformation rather than information.

Until direct correlation is shown between a given accelerated test and a given service the accelerated test is chiefly valuable for what it indicates rather than what it might at first sight appear to prove. Accelerated tests which do have direct correlation are badly needed and much work is being done to find such tests. Some accelerated tests certainly give useful information, whether or not they correlate exactly with service results. To date, however, much of the corrosion data in the literature, whether based on laboratory tests or service records, has to be read with the realization that under conditions other than those to which the data refer, different results might be obtained.

Nevertheless the opinions and information published on the performance of various classes of material in service or in laboratory tests may be of use, and a selected bibliography of about 300 titles in scientific and technical literature is appended. No attempt is made to cover the voluminous literature of corrosion in general, although reference is made to a few books, bibliographies and general articles which will serve as introduction to a study of the general corrosion problem. The aid of the metallurgical departments of representative producers of the various types of ferrous products has been enlisted in the preparation of the bibliography, in order to avoid the omission of important articles recording tests especially favorable or unfavorable to any particular type of product.

It should be pointed out that while iron or steel protected by suitable coatings such as paint, renewed as needed, or by a heavy coating of zinc or cadmium may often, in normal uses and normal locations, be the cheapest in respect to cost vs. life, yet they are inherently corrodible. When corrosive conditions are severe it is often good economy to select a more expensive material which is inherently resistant to that type of corrosion in question and which need not depend so completely on protective coatings for long life.

While small additions of other elements such as copper, molybdenum, etc., may slightly reduce the rate of corrosion of iron or steel, to secure anything approaching complete resistance under severe conditions either ferrous alloys of entirely different types from ordinary iron or steel, or non-ferrous alloys, are generally required. Iron or steel with approximately 14% silicon, or 15% chromium or 30% nickel, has an entirely different order of resistance to corrosion than have the common iron and steel products. Aluminum and its alloys, copper, brass, bronze, lead, nickel and its alloys, tin and zinc, beside the noble metals, all show corrosion-resistance of very high order under appropriate conditions.

Each of the metals and alloys is well able to resist corrosion under some conditions and poorly able to resist it under others. To defeat corrosion one must adapt the materials to the conditions of service or alter the conditions to meet the requirements of the material.

CONTENTS

	Page
Treatises, General and Introductory Papers on Corrosion - - - - -	9
Bibliographies - - - - -	9
Books - - - - -	9
Monographs - - - - -	10
Symposia on Corrosion - - - - -	11
Continued Reports - - - - -	11
General Articles - - - - -	11
Effect of Impurities and of Additions such as Copper to Iron and Steel - - - - -	17
Corrosion of Cast Iron and Comparison of Cast Iron with Other Ferrous Products - - - - -	23
Comparison of Wrought Iron and Commercially Pure Iron with Other Ferrous Products - - - - -	26
Corrosion in Automotive Engines - - - - -	28
Chromium Steels - - - - -	29
Nickel Steels - - - - -	32
Silicon Irons and Steels - - - - -	33
Corrosion of Zinc Coated Irons and Steels - - - - -	34
Non-Ferrous Alloys - - - - -	36

Treatises, General and Introductory Papers on CorrosionBibliographies

Bibliography on metal corrosion and protection, 2d Edition,
Carnegie Library, Pittsburgh, 1909.

Bibliography on corrosion of metals and its prevention,
N. VanPatten, Mass. Inst. Tech. Cambridge, Mass. 1923.
(comprehensive and quite complete to 1923).

Research Information surveys on corrosion of metals,
H. F. Whittaker, National Research Council,
Washington, D. C.

- No. 1. Nickel 1923
- No. 2. Aluminum 1923
- No. 3. Copper, 1923
- No. 4. Zinc 1924 (revised and published 1926 by
Am. Zinc Inst.)
- No. 5. Tin 1924
- No. 6. Lead 1924

Bibliography of chemical corrosion,
W. S. Calcott, J. C. Whetzel - Trans. Am. Inst. Chem.
Eng. 15, pt. 1, 1923, p. 83.

Books

- 1910 Corrosion and preservation of iron and steel (with
bibliography)
A. S. Cushman, H. A. Gardner, McGraw Hill Co.,
New York City.
- 1911 The corrosion of iron and steel,
J. A. N. Friend, - Longmans & Co., London.
- 1923 Corrosion tests and materials of construction for
chemical engineering apparatus.
W. S. Calcott, J. C. Whetzel, H. F. Whittaker, -
Am. Inst. Chem. Eng.
- 1923 The causes and prevention of corrosion,
A. A. Pollitt, - E. Benn, Ltd., London.
- 1923 The chemical resistance of engineering materials,
M. L. Hamlin, F. M. Turner, Jr. - Chemical Catalog
Co., New York.
- 1925 Acid resisting metals,
S. J. Tungay - E. Benn. Ltd., London.
- 1925 The corrosion of metals,
U. R. Evans, - E. Arnold & Co., London.

Books (cont'd).

- 1926 Corrosion - causes and prevention, (in press)
F. N. Speller - McGraw-Hill Book Co., New York.

Monographs

- 1922 Protective metallic coatings for the rustproofing of iron and steel,
Bureau of Standards Circular 80, Superintendent of Documents, Government Printing Office, 20¢
- 1922 Corrosion tests on metals and alloys in acid mine water from coal mines,
W. A. Selvig, G. M. Enos, - Carnegie Inst.
Tech. Bulletin No. 4.
- 1922 The corrosion of iron,
J. N. Friend - Iron and Steel Inst., Carnegie Schol. Mem. 11, Spon & Chamberlain, New York (chiefly on cast iron)..
- 1923 Microstructural aspects of metals and alloys corroded by acid mine water,
R. J. Anderson, G. M. Enos - Carnegie Inst.
Tech. Bull. No. 5.
- 1923 Corrosion and preservative coatings,
F. N. Speller - Kents Mech. Eng. Handbook p.437.
- 1923 Second report on relative corrodibility of various commercial forms of iron and steel,
J. N. Friend, Iron and Steel Inst., Carnegie Schol. Mem. 12. Spon & Chamberlain, New York.
- 1925 Protection of oil and gas field equipment against corrosion,
R. Van A. Mills, U. S. Bureau of Mines Bull No. 233; Superintendent of Documents, Government Printing Office. 35¢

A German journal, Korrosion und Metallschutz, Berlin, is now published which deals solely with corrosion and its prevention.

Symposia on Corrosion

- 1908 Trans. American Electrochemical Society, 19, p. 151.
 1915 Engineer, 130, p. 571
 1916 Journal Faraday Society, 11, p. 163.
 1921 American Electrochemical Society, 39, p. 9.
 1923-4 Journal Faraday Society, 19, p. 156, 839.
 1923 Industrial and Engineering Chemistry, 15, p. 127.
 1923 Chemical and Metallurgical Engineering, 28, p. 678-86
 1924 Corrosion Resistant, Heat-Resistant, Electrical Resistance Alloys, A. S. T. M. 24, (2) p. 189.

Continued Reports

- 1918-1925+ Proc. A. S. T. M., Reports, Com. A-5
 1920-1925+ Proc. Inst. Civil Eng. (British),
 Deterioration of structures of timber, metal
 and concrete exposed to the action of sea
 water.
 1924-1925 American Foundrymen's Association

General Articles

- 1900 Untersuchungen über den Angriff des Eisens durch
 Wasser,
 E. Heyn, - Mitt. Koeniglichen Technischen Ver-
 suchaustalten, 18, 38.
 1908 Über den Angriff des Eisens durch wasserige Lösun-
 gen, E. Heyn, O. Bauer, - Mitt. Koniglichen Mater-
 ialprüfungsamt 26, p. 1-104; Stahl u. Eisen 28, 1564;
 Jour. Iron and Steel Inst. 78, p. 663.
 1909 On the corrosion of iron in water and aqueous solu-
 tions,
 E. Heyn, O. Bauer, Proc. 5th Cong. Inst. Assn.
 Test. Materials Section, 17, p. 21.

- 1910 Über den Angriff des Eisens durch Wasser und Wasserige lösungen,
Mitt. Koeniglichen Materialprüfungsamt 28, p.62.
- 1910 Corrosion of iron and steel,
A. Sang. - Hill Publishing Co.; American Chemical Society, Abstracts 4, p. 1451.
- 1912 Corrosion of steel and its prevention,
A. S. Cushman - Iron Age, 83, p. 1278.
- 1913 Corrosion of iron and steel,
W. H. Walker, - Iron Age, 91, p.1205; Sci. American, 8.76 p.51.
- 1913 Electrolytic theory of the corrosion of iron,
B. Lambert - Met. & Chem. Eng. 11, 272.
- 1913 Steel and its corrosion,
Eng. Magazine, . 45, p. 569.
- 1913 Electrolytic theory of the corrosion of iron,
B. Lambert, Met. & Chem. Eng. 11, p. 272.
- 1914 Corrosion of boilers through the use of sulphurous oils,
Int. Marine Eng. 19, p. 221.
- 1914 Corrosion test of metal lath in stucco,
J. C. Pearson - Concrete Cement, 5, p. 38.
- 1914 Iron and steel processes and their relation to corrosion,
J. T. Hay,- Munic. Eng. 46, p. 276.
- 1914 Tests of the resistance to corrosion of various brands of iron and steel,
Eng. News 72, p. 255; American Gas Light Journal, 101, p. 149.
- 1915 Corrosion problem before the American iron and steel,
Inst., Met. & Chem. Eng., 13, p. 420.
- 1915 Bibliography of metal corrosion and protection,
Eng. Soc. W. Pa. 31, p. 193.
- 1915 Corrosion of iron,
L. C. Wilson - Eng. Mech. 48, p.517, 667, 849
49, p.58, 202.
- 1915 Corrosion of pure irons and steels used by U. S. Reclamation Service,
Eng. News, 74, p. 78
- 1916 Corrosion of 350 mile Australian steel pipe line 12 years old,
P. V. O'Brien, - Eng. Record, 74, p.501.

- 1916 Observations upon the atmospheric corrosion of commercial sheet iron,
E. A. Richardson, L. T. Richardson, - Met. & Chem. Eng. 15, p. 450.
- 1916 Rustless ferro alloys,
L. Aitchison, Eng. 21, p.329, 351.
- 1916 The relative corrodibilities of iron and steel,
J. N. Friend, - Faraday Soc. 11, p. 204.
- 1916 Theory of the corrosion of steel,
L. Aitchison, Jour. Iron and Steel Inst. 93, (1).p.77.
- 1916 Corrosion of iron,
L. C. Wilson, - Engng. Mag. New York, 178; Chem. Abstract, 1916, p. 1744.
- 1918 Corrosion of iron in contact with other metals and alloys,
O. Bauer, O. Vogel, - Mitt. Kgl. Mat. Prof. 36, p. 114; Zeit. Met. 10, 1919, p. 124; Stahl u. Eisen 40, 45, 85, 1920.
- 1918 Corrosion of iron and steel with special reference to reinforced concrete: Abstracts,
J.N. Friend, Iron Age, 101, 444, Eng. 24, p.550.
- 1919 Corrosion-proof steels, recent progress in the development of iron alloys that resist rust,
Sci. American, 121, p.156.
- 1919 Effect of rolling on rusting of iron and steel,
H. Y. Carson, Eng. & Contr. 51, p. 225.
- 1920-
- 1925 Deterioration of structures exposed to sea-water,
Inst. Civ. Eng. 1920; Eng. 138, p.91, 1923;
Eng. 118, p. 774, 1924; Engng. 119, p. 21, 1925.
- 1920 Experiments on the corrosion of iron and steel,
W. D. Richardson, Am. Inst. Chem. Eng. 13, (1), 169.
- 1920 Rates of solution of iron and steel in non-oxidizing and oxidizing acids,
W. D. Richardson, - Am. Inst. Chem. Eng. Trans. 13 (1) p. 265.
- 1920 Suggestion basis for an index of corrosion for iron and steel,
W. D. Richardson, - Am. Inst. Chem. Eng. Trans. 13, (1) 277.

- 1921 Introduction to symposium on corrosion of iron and steel,
W. H. Walker, - Am. Electrochem. Soc. 39, p. 53.
- 1921 Preventing corrosion of iron and steel,
F. N. Speller, Am. Electrochem. Soc. 39, p. 141.
- 1922 Corrosion of iron and steel,
T. S. Fuller, - Gen. Electrical Rev. 25, p. 425.
- 1922 Corrosion of iron by natural waters,
Chem. & Met. Eng. 27, p. 592.
- 1922 Corrosion of various steels,
Iron Trade Rev. 70, p. 1475; Blast Furnace and Steel Plant 10, p. 346.
- 1922 Corrosion with special reference to the ferrous metals and the deterioration of ships.
A. Pickworth, Electrician 88, p. 100.
- 1922 Pitted corrosion of mixture iron,
D. M. Strickland, - Gas Age 49, p. 623.
- 1922 Modern conceptions of corrosion,
W. Ramsay, Liverpool Engineering Soc. 43, p. 63.
- 1922 Corrosion of ferrous materials,
R. A. Hadfield, Inst. Civil Eng.; Engng. 113, p. 419; Met. Ind. London, 20, p. 381.
- 1923 Corrosion of iron in water and neutral salt solutions,
J. N. Friend, - Jour. Chem. Soc. 123, p. 2996.
- 1923 Corrosion of rustproofed iron and steel,
W. P. Wood, - Chem. & Met. Eng. 28, p. 769.
- 1923 Corrosion of electrolytic iron,
W. E. Hughes, - Chem. & Met. Eng. 29, p. 536.
- 1923 Corrosion of iron and steel,
C. L. Wright - Locomotive 34, p. 131.
- 1923 Corrosion-resisting irons and steels,
J. A. Aupperle - Chem. & Met. Eng. 28, p. 681.
- 1923 Effect of velocity on the corrosion of steel in sulphuric acid.
W. G. Whitman, et al. Ind. & Eng. Chem. 15, p. 672.
- 1923 How iron rust grows,
A. Gradenwitz - Sci. American 128, p. 183,
British World 19, p. 123.

- 1923 Mechanism of the corrosion of iron and steel in natural waters and the calculation of specific rates of corrosion,
R. E. Wilson, - Ind. & Eng. Chem. 15, p.127.
- 1924 The submerged corrosion of iron,
W. G. Whitman, R. P. Russell, - Chem. & Industry, June 20, 27; July 4, 11.
- 1924 Effect of hydrogen ion concentration on the submerged corrosion of steel,
G. W. Whitman, R. P. Russell, V. J. Alter - Ind. & Eng. Chem. 16, p. 665.
- 1924 Electrolytic theory of corrosion,
F. N. Speller, F. G. Harmon - Am. Electrochem. Soc. 46, p. 313.
- 1924 Prevention of corrosion of iron and steel,
C. P. Perrin, - Eng. & Engng. p. 223.
- 1924 Effect of alkaline solutions on steel immersed in water,
F. N. Speller, E. R. Texter, - Ind. & Eng. Chem. 16, p. 393.
- 1924 The electrolytic theory of corrosion,
W. D. Bancroft, Journal Physical Chem. 28, p.785.
- 1924 Critical resume of information on corrosion of iron and steel,
British Elect & Allied Ind. Res. Council; World Power 2 p. 146; Chem.Abst. 18, p. 3353.
- 1924 Film protection as a factor in corrosion,
F. N. Speller, - Am. Electrochem. Soc. 46, p.225.
- 1925 Turbine blade corrosion prevented by eliminating oxygen,
W. R. Whitney, - Power 62, July 21, p. 113.
- 1925 Corrosion of iron,
W. R. Whitney, - Ind. & Eng. Chem. 17, p.385.
- 1925 Corrosion of iron in absence of oxygen,
J. W. Shipley, I. R. McHaffie, N. D. Clare, - Ind. & Eng. Chem. 17, p. 381.

- 1925 The causes and effects of corrosion,
R. J. McKay - Chem. Met. Eng. 32, p. 432.
- 1925 Corrosion,
E. C. Trax - Jour. Am. Water Works Assoc.
14, p. 255.
- 1925 Causes and controlling factors in the corrosion of
iron and steel,
W. P. Wood, - Trans. A. S. S. T. 7, p. 321.
- 1925 Electrolytic corrosion of ferrous metals,
W. M. Thornton; J. A. Harle, - Engng. 119, p. 237;
Trans. Faraday Soc. 21, p. 23; Journal Iron and
Steel Inst. 111 p. 547.
- 1925 Water-line corrosion of iron and steel,
U. R. Evans, Jour. Soc. Chem. Ind. 44, p. 163;
Jour. Iron and Steel Inst. 111 p. 538.
- 1925 Corrosion of Iron and Steel -
T. S. Fuller - American Soc. for Steel Treating,
Handbook, p. A45-50.
- 1926 Factors other than dissolved oxygen influencing
the corrosion of iron pipes,
J. R. Bayles, - Ind. Eng. Chem. 18, p. 370.
- 1926 Boiler water conditioning with special reference
to high operating pressures and corrosion,
R. E. Hall, - Mech. Eng. 48, p. 317.

Effect of Impurities and of Additions such as Copper to Iron and steel.

- 1900 Influence of copper in retarding corrosion of soft steel and wrought iron,
F. H. Williams, Eng. Soc. West Pa. 16, p.231;
Iron Age 66, p. 16.
- 1901 Effect of copper on steel for wire making,
Stead & Wigham, - Iron and Steel Inst. 1901,
II, p.122.
- 1904 Das Verhalten einiger Metalle im See Wasser
Stahl u. Eisen, 24, pp. 561, 629.
- 1905 Über den Einfluss der Reihenfolge von Zusätzen zum
Flusseisen auf die Widerstandsfähigkeit gegen ver-
dünnte Schwefelsäure,
O. Bauer, - Mitt. Königlichen materialprüfungsamt
23, p. 292
- 1907 Corrosion tests on copper steels as rolled,
P. Breuil - Jour. Iron & Steel Inst. 74, p.60.
- 1907 Copper steels,
P. Breuil - Jour. Iron & Steel Inst. II, p.1.
- 1907 Relative rates of corrosion of acid and basic steel,
G. A. Fraser, Iron Age, 79, p. 1193.
- 1911 Influence of impurities on the corrosion of iron,
J. W. Cobb, - Jour. Iron & Steel Inst. 1 p. 170.
- 1911 The marked influence of copper in iron and steel on
the acid corrosion test,
W. H. Walker, - A. S. T. M. p. 615.
- 1911 Prevention of corrosion in metal lath,
C. W. Noble, - Can. Eng. 20 p. 506.
- 1912 Influence of carbon on the corrodibility of iron,
C. Chappel, - Jour. Iron & Steel Inst. 85, I,
p. 270.
- 1913 Copper bearing steel and corrosion,
Iron Age 92, p. 572.

- 1913 Influence of copper in retarding the corrosion of steel plate,
Eng. News, 70, p. 232.
- 1913 Properties of mild steels as influenced by the addition of small amounts of copper,
G. H. Taylor, - Mass. Inst. Tech. Thesis.
- 1913 Pure iron vs copper-bearing steel,
A. S. Cushman, - Inst. Ind. Research Bull. 5.
- 1913 Influence of silicon on the corrosion of cast iron,
J. N. Friend, Jour. Iron & Steel Inst. 87, (1) p. 382.
- 1913 Copper in steel, the influence on corrosion,
D. M. Buck, Jour. Ind. & Eng. Chem. 5, p. 447.
- 1913 Influence of various elements on the corrodibility of iron and steel,
C. F. Burgess, J. Aston, Jour. Ind. & Eng. Chem. 5, p. 458.
- 1913 Influence of copper upon the physical properties of steel,
A. S. Cushman, R. W. Hunt, - A. I. M. M. E., 84, p. 2936 (bulletin).
- 1914 Data on the influence of copper on the corrosion of iron and steel,
E. R. Hamilton, Am. Gas Light Jour. 100 p. 247, 250.
- 1914 Influence of molybdenum upon the corrodibility of steel,
J. N. Friend, C. W. Marshall, - Jour. Iron & Steel Inst. 89, (1) p. 503.
- 1915 Influence of different elements upon the corrosion of iron,
L. C. Wilson, Eng. Mag. 50, p. 78.
- 1915 Effect of Various Elements in Steel on its resistance to corrosion,
Eng. & Contr. 44, p. 64.
- 1915 Experiments on the rusting of iron in water which has been softened by the permutit process and means for preventing it,
O. Bauer, E. Wetzell, Mitt. Koniglichen Materialprufungsamt 33 p. 1, (also Z. F. Metallk 10, 51, 1919).

- 1915 Recent progress in corrosion resistance,
D. M. Buck, - Am. Iron and Steel Inst. Yearbook,
p. 212.
- 1916 Influence of carbon and manganese upon the corrosion
of iron and steel,
R. A. Hadfield, J. N. Friend, - Jour. Iron and Steel
Inst. 93, (1) p. 48; Eng. 121, p. 528.
- 1916 Research on the corrosion resistance of copper steel,
D. M. Buck, J. O. Handy, Jour. Ind. & Eng. Chem.
8 p. 209.
- 1916 The effect of rust on the corrosion of iron and steel,
J. Aston, Am. Electrochem. Soc. 29, p. 449.
- 1916 Discussion of "atmospheric corrosion of sheet iron",
Trans. Am. Electrochem. Soc. 30, p. 390.
- 1916 Observations on the atmospheric corrosion of com-
mercial sheet iron,
E. A. Richardson, L. T. Richardson, - Am. Electro-
chem. Soc. 30, p. 379.
- 1916 Corrosion of ingot iron containing cobalt, nickel or
copper,
H. T. Kalmus, K. B. Blake, Proc. Am. Inst. Chem.
Eng. 9, p. 233. (Also Jour. Ind. & Eng. Chem. 9,
p. 123, 1917 and Iron Age 99 p. 201, 1917.
- 1917 Corrosion of ingot ^{iron} ~~copper~~ containing cobalt, nickel
or copper,
A. S. Cushman, H. T. Kalmus, Jour. Ind. & Eng.
Chem. 9, p. 414.
- 1917 Corrosion of fence wire,
O. W. Storey, - Trans. Am. Electrochem. Soc. 32,
p. 285 (later data contained in a privately
printed pamphlet N-716, C. F. Burgess Laboratories,
Madison, Wisc. 1926; Iron Age 117, 1926, p. 424.
- 1918 The effect of the presence of a small amount of cop-
per in medium carbon steel,
C. R. Hayward, A. B. Johnston, Bull. A. I. M. M.
E. p. 159; Iron Trade Rev. 62 p. 320.

- 1919 Exposure tests on sheeting material,
S. L. Hoyt, - Chem. & Met. Eng. 21, p. 142.
- 1919 Influence of very low percentages of copper in
retarding the corrosion of steel,
A. M. Buck, - Proc. A. S. T. M. 19, (2) p.224.
- 1919 Further data on the effect of copper in reducing
corrosion of steel,
Eng. News Record 83, p. 14.
- 1919 Copper bearing sheets,
Iron Age, 104, p. 44.
- 1920 Copper in steel tie plates reduces corrosion,
Eng. Contractor 54, p.256; Railway Age 69, p.146
- 1920 Copper-steel as a rust resisting metal,
Can. Eng. 39, p.300
- 1920 Influence of copper, manganese and chromium and
some of their combinations on the corrosion of iron
and steel,
E. A. Richardson, L. T. Richardson, Am. Electro-
chem. Soc. 38, p. 221.
- 1920 Review of the development in copper steel,
D. M. Buck, - Iron Age 106, p. 1109; Yearbook
Am. Iron & Steel Inst. p. 373.
- 1921 Influence of copper on some physical properties of
iron and steel,
E. A. Richardson, L. T. Richardson, - Chem. Met.
Eng. 24, p. 565.
- 1921 Experiments on the corrosion of iron and steel,
T. S. Fuller, Am. Electrochem. Soc. 39, p. 199.
- 1921 Principles of alloying to resist corrosion,
O. P. Watts, - Trans. Am. Electrochem. Soc. 39,
p. 253.
- 1921 Some observations on the mechanism of increased corro-
sion resistance of steel and iron due to small copper
content,
D. M. Buck, - Am. Electrochem. Soc. 39, p.109.
- 1921 Transformer tanks of copper-alloy steel,
R. V. Bingay, - Elec. Review, 79, p. 102.

- 1921 The gap between theory and practice in the production of corrosion-resisting iron and steel,
W. D. Richardson, - Am. Electrochem. Soc. 33,
p. 61.
- 1921 Anomalies encountered in a study of immersion tests of iron and steel,
A. S. Gushman, G. W. Coggeshall, - Am. Electrochem. Soc. 33, p. 81.
- 1921 Observations on the corrosion of iron and steel,
J. A. Aupperle, D. M. Strickland, - Am. Electrochem. Soc. 39, p. 123.
- 1921 The corrosion of old iron,
E. A. Richardson, L. T. Richardson, - Am. Electrochem. Soc. 39, p. 167.
- 1921 Observations on the mechanism of the increased corrosion resistance of steel and iron due to small copper content,
D. M. Buck, - Am. Electrochem. Soc. 39, p. 47.
- 1921 Rostversuche mit Kupferhaltigen Eisenblechen,
O. Bauer, Stahl u. Eisen 41, pp. 37, 76, Jan. 13, 20;
Mitt. Koeniglichen Materialprüfungsamt, 58, p. 85,
(1920).
- 1921 Rusting of steel containing copper,
Engng. 111, 213, Feb. 18; Eng. and Contractor 55,
p. 329.
- 1921 Some advantages claimed for copper alloy steel,
R. V. Bingay, - Elec. World, 78, p. 425.
- 1921 Copper in steel and the corrosion of cars,
Brass World, 17, p. 65.
- 1921 The corrosion of steel ranges,
O. W. Storey, - Am. Electrochem. Soc. 29, p. 175.
- 1922 Control of Corrosion by deactivation of water,
F. N. Speller, J. Frank. Inst. 193, p. 515.

- 1923 Reducing the corrosion in steel cars,
J. J. Tatum, Railway Age, June 16, p. 1437.
- 1923 Influence of copper on the corrosion of steel,
R. C. Case - Railway Mech. Eng. 97, p.408.
- 1923 Influence of copper on iron and steel,
W. Guertler, Norges Geol. Undersokelse 117; Chem.
Abst 19, Apr. 10, 1925, p. 1121.
- 1924 How the ravages of corrosion can be reduced,
C. A. McAllister, Marine Eng. 29, p.333.
- 1924 Copper in modern steels, II. Corrosion,
G. K. Fertig, - Tech, Engng. News, Sept.5, 1909,30.
- 1924 Tests steel plates of Leviathan,
G. J. B. Waterhouse, - Iron Trade Review, 75, 229.
- 1925 Anti-corrosion of 1.67% copper steel in bottom plates
of ships,
Brass World 21, Mar. p. 178.
- 1925 Rust-proofing of materials,
M. E. McDonnell, Mech. Eng. 47, 875, Railway Age
79, p.849.
- 1925 Copper-bearing steel for structural purposes,
F. P. Turner, Chairman Sub-Committee, Bull. Am.
Ry. Eng. Assn. 27, No. 230, p. 112 (Oct.1925)
- 1926 Effect of brine drippings on track appliances and
tests of tie-plates subject to brine drippings -
E. D. Swift, Chairman, Sub-Com. Bull. Am. Ry.
Eng. Assn. 27, No. 283 (Jan. 1926) p.647.

Corrosion of Cast Iron and Comparison of Cast Iron with Other Ferrous Products.

- 1893 Action of sea water on cast iron and wrought iron,
R. Mallet, - Report 8th Meeting British Assn.
Adv. Sci. p. 253.
- 1910 Corrosion of a cast iron pipe by fresh water,
T. Steel, - Jour. Soc. Chem. Ind. 29, Pt.2,
p. 1141.
- 1912 Corrosion of cast iron and lead pipe in alkaline
soils,
Jour. Soc. Chem. Ind. 41, p. 3117.
- 1913 Corrosion of cast iron reviewed,
R. H. Gaines, - Iron Age 91, p. 1358.
- 1913 Prevention of the corrosion of iron water mains,
W. T. Montfort, - Eng. News, 70, p. 570.
- 1914 External corrosion of cast iron pipe; abstracts,
M. R. Pugh, - Munic. J. 37, p. 424. Am. Soc.
Mech. Eng. Jour. 36, p. C199;
Eng. & Contr. 42, p. 377; Am. Gas Light Jour.
103, p. 65.
- 1915 Corrosion of iron and steel pipe,
W. A. Dunkley, J. E. Noble, Power, 41, p. 534.
- 1915 Corrosion of steel and cast iron compared,
R. C. McWane, H. Y. Carson, - Foundry 43, p. 467;
Iron Trade Review 58, 1915, p. 1417.
- 1915 The relative corrodibilities of gray cast iron
and steel,
J. N. Friend, C. W. Marshall, Iron and Steel
Inst. (1) p. 353; Gas World 62, p. 579;
Iron Age, 95, p. 1114.
- 1916 Corrosion of cast iron,
O. Bauer, E. Wetzel, - Mitt. Koniglichen
Materialprüfungsamt 34, 11; Iron Age 99, p. 253.

- 1917 Cast iron and its rust-resisting power,
E. A. Richardson, L. T. Richardson, - Iron
Trade Rev. 61, p. 834.
- 1917 Air in water causes pipe corrosion,
H. A. Holmes, Electrical World, 69, p. 319.
- 1917 Corrosion of cast iron and its bearing upon the
electrolytic theory of corrosion,
E. A. Richardson, L. T. Richardson, - Met.
and Chem. Eng. 16, p. 582.
- 1917 Rusting of pipe in service,
H. Y. Carson, - Am. Water Works Assn. Journal.
4, p. 252.
- 1917 Corrosion of cast iron, - E. A. Richardson and
L. T. Richardson, - Trans. Am. Electrochem. Soc.
31, p. 191.
- 1918 Relative corrosion of cast iron, wrought iron and
steel pipe in house drainage system,
W. P. Gerhard, J. Am. Soc. Mech. Eng. 40, p. 945.
- 1918 Corrodibility of cast iron,
Sci. Am. Sup. 85, p. 333.
- 1919 Self corrosion of cast iron and other metals in
alkaline soils,
W. N. Smith, - Electric Railway Journal 58, p. 911.
- 1921 Corrosion in iron and steel pipe,
Textile World, 60, p. 2873.
- 1921 Graphitic corrosion of cast iron,
J. V. Davies, - Iron Age 108, p. 942.
- 1921 Control of corrosion in iron and steel pipe,
F. N. Speller, Can. Eng. 40, p. 359; Mech. Eng.
43, p. 661.

- 1922 Corrosion of cast iron in alkaline soils,
Engng. 113, p. 36.
- 1922 The corrosion of iron,
J. M. Friend, - Iron and Steel Inst., Carnegie
Schol. Mem. 11, Spon & Chamberlain, New York.
- 1922 Why superheated steam causes failure of cast iron,
Sci. Am. 127, p. 331.
- 1923 Corrosion of cast iron,
H. Y. Carson, - Trans. Am. Foundrymen's Assn.
30, p. 206.
- 1923 Corrosion of iron, particularly iron conduits,
P. Medinger, Rev. Univ. Mines 18, p. 227;
Chem. Abst. 18, 1924, p. 1462.
- 1924 A critical resume of information on corrosion of
iron and steel with special reference to cast
iron in sea water.
World Power 2, 146-55.
- 1924 Graphitic softening of cast iron,
J. W. Shipley, I. R. McHaffie, -Ind. Eng. Chem.
16, p. 573.
- 1924 Corrosion of cast iron by (Buenos Aires) tap water,
C. F. Hickethier, Anal. Assoc. Qu. Argent 11, p.
364; Chem. Abst. 19, p. 3245 (1925).
- 1926 Flow tests of old cast iron water mains,
J. B. Eddy, - Chicago Water Works;
Eng. News-Record 96 p. 287.

- Comparison of Wrought Iron and Commercially Pure Iron with
Other Ferrous Products (see also effect of impurities and additions).
- 1881 On the comparative endurance of iron and steel when exposed to corrosive influences,
 D. Phillips; - Proc. Inst. Civil Eng. 65, p.73.
 - 1895 Relative corrosion of wrought iron and steel,
 H. M. Howe, - Mineral Ind. 4, p. 429.
 - 1900 Relative corrosion of wrought iron, soft steel and mild steel,
 H. M. Howe, Eng. Min. Journal, 70 p. 188.
 - 1905 Manufacture and characteristics of wrought iron,
 J. P. Roe, Trans. Am. Inst. Min. Eng. 36, p.203,
 p. 814. (discussion)
 - 1906 Relative corrosion of wrought iron and steel,
 H. M. Howe, Proc. Am. Soc. Test. Mat. 6, p. 155.
 - 1907 Corrosion of iron and steel,
 F. N. Speller, Proc. Eng. Soc. West Pa. 22,
 p. 472; Iron Age 73, p. 478.
 - 1908 Relative corrosion of steel and wrought iron tubing,
 H. M. Howe, B. Stoughton, Proc. Am. Soc. Test. Mat. 8, p. 247.
 - 1908 Über den Angriff des Eisens durch Wasser und wasserige Lösungen,
 E. Heyn, O. Bauer, Mitt. Koeniglichen Materialprüfungsamt 26 p. 1; 28, 1910 p.62.
 - 1909 On the corrosion of iron in water and aqueous solutions, - Proc. 5th Cong. Inst. Assn. Test. Materials Sec. 17.
 - 1911 Pure iron water pipe to resist corrosion,
 D. W. Murphy, - Eng. Record 64, p. 41.
 - 1912 Relative corrosion of iron and steel pipe as found in service,
 W. H. Walker, Jour. New Eng. Water Works Assn. 26, p. 7; Jour. Ind. and Eng. Chem. 4 p.486.

- 1912 Comparative service obtained with wrought iron and soft steel pipes as water lines in the U. S.
F. N. Speller, Proc. 6th Cong. Int. Assn. Test. Mat. Sec. 24.
- 1912 Wrought iron, steel and corrosion,
W. R. Fleming, - Iron Age 89, p. 333.
- 1913 Steel, wrought iron and corrosion,
G. Schulmann, - Iron Age 92, p. 1190.
- 1915 Corrosion of iron and steel pipe,
W. A. Dunkley, J. E. Noble - Power 41, p. 584.
- 1915 Wrought iron or steel pipes,
L. C. Wilson, Eng. News, 50, p. 247.
- 1916 Corrosion of wrought iron,
Iron Age 97, p. 1445.
- 1917 Slag and rust resistance of wrought iron,
Gas Age 39, p. 431.
- 1919 Influence of enclosed slag on the corrosion of wrought iron,
L. T. Richardson, Tr. Am. Electrochem. Soc. 37, p. 529.
- 1921 Experiments on the corrosion of iron and steel,
W. D. Richardson, - Trans. Am. Inst. Chem. Eng. 13, pt. 1, 169; Chem. Met. Eng. 23, 1920, p. 343.
- 1921 Observations on the corrosion of iron and steel,
J. A. Aupperle, D. M. Strickland, - Trans. Am. Electrochem. Soc. 39, p. 167.
- 1921 Self corrosion of iron and steel pipes,
A. D. Flinn, - Trans. Am. Waterworks Assn. 8, p. 630.
- 1922 Pitted corrosion of impure iron,
D. M. Strickland, - Gas Age 49, p. 623.
- 1923 Corrosion of electrolytic iron,
W. E. Hughes, Chem. Met. Eng. 29, p. 536.

- 1924 Soil corrosion of gas distributing system,
H. S. Christopher - Gas Age 54 p. 633.
- 1924 Corrosion of iron pipes,
Krohnke, Wasser u. Gas 14, 234; Jour. Iron
and Steel Inst. 111, p. 600.
- 1925 The corrosion problem in connection with water-
works engineering,
F. W. Speller, Jour. New Eng. Water Works Assn.
39, No. 1, p. 90.
- 1925 Half of Lowell service pipes changed within 52 years,
R. J. Thomas, Eng. News Record 95, p. 1041.
- 1925 The corrosion and rusting of wrought iron and steel
gas barrel - A. Stokes - Report of Wrought Iron
Tubing Inquiry Comm. Gas Journal (Supp) 171, p.3.

Corrosion in Automotive Engines.

- 1924 Undue wear of engine parts is caused by rust,
Automotive Industries, page 353.
H. C. Mougey and E. S. Patch.
- 1924 Scuffed Pistons result from cold jacket and lack
of oil,
F. Jardine, Automotive Industries, Vol. 51, p.242.
- 1925 Engine corrosion - Its causes and avoidance,
F. Jardine, - Journal of Society of Automotive
Engineers, Vol. 17, p. 605.
- 1926 Notes on crankcase corrosion,
M. A. Thorne, - Jour. of Soc. of Automotive
Engineers, Vol. 18, p.35.

Chromium Steels.

- 1912 Corrosion of nickel, chromium and nickel-chromium steels,
J. N. Friend, J. L. Bentley, W. West, -
Jour. Iron and Steel Inst. 85, p.249 (1); 87 (1)
p. 388.
- 1915 Non-rusting alloys - Iron Age 36, p. 881.
- 1916 Corrosion of high chromium steels,
R. A. Hatfield, - Iron Age 97, p. 202.
- 1920 Stainless steel, its treatment, properties and applications,
W. H. Marble, Am. Soc. Steel Treat. 1, 170.
- 1920 Stainless steel,
J. H. G. Moneypenny, - Jour Soc. Chem. Ind. 39,
390R.
- 1920 Non-rusting chrome-nickel steels,
B. Strauss, - Naturwissenschaften 8 p. 812.
- 1921 Chromium steels and irons,
L. Aitchison, - Engng. 112, p. 805.
- 1921 Stainless steel for turbine blades,
T. Firth, - Electrician 87, p. 540.
- 1921 Stainless steel, C. Guff, Prac. Eng. 64 p.379.
- 1921 Stainless steel composition and properties,
E. Haynes, Iron Age 107, 1467; Blast Furnace
and Steel Plant 9, p. 348.
- 1922 L'acier Stainless,
H. Huber, - Rev. Univ. Mines 6th series, 13,
p. 19.
- 1922 Corrosion of chrome steels,
Sci. Am. 127, p. 95.
- 1922 Corrosion of chromium steels,
Jour. Soc. Auto. Eng. 10, 414.
- 1922 Resistance to corrosion of various types of chromium steels,
H. S. Rawdon, A. I. Krynetsky, - Chem. Met.
Eng. 27, July 26, p. 171

- 1923 Resistance to corrosion of stainless steel and iron,
J. H. G. Moneypenny, - Faraday Soc. 19 p.169.
- 1923 Chromium iron alloy resists oxidation, corrosion, abrasion and heat,
Coal Age 23, p. 174.
- 1923 Corrosion resisting irons and steels,
J. A. Aupperle, - Chem. Met. Eng. 28, p. 681.
- 1923 Heat and acid resisting alloys (Ni-Cr-Fe),
J. F. Kayser, - Faraday Soc. 19, p. 184.
- 1924 Stainless steels, their heat treatment and resistance to sea-water corrosion,
J. Strauss, J. W. Talley, - A. S. T. M. 24, (2) p. 217.
- 1924 Corrosion-resistant alloys - past, present and future with suggestions as to future trend,
P. A. E. Armstrong, - Proc. A. S. T. M. 24 (2) p. 193.
- 1924 Ferrous alloys resistant to corrosion,
Sakaltwalla, - Iron Age 113, p. 1209; Chem. Met. Eng. 20; British World 20 p. 125; Foundry Trade Journal p. 156.
- 1924 Tests for grading corrosion resisting alloys,
W. E. Erikson, L. A. Kirst, - Trans. Am. Electrochem. Soc. 46, p. 339.
- 1924 Symposium on corrosion resistant "heat resistant and electrical resistance alloys", - Proc. A. S. T. M. 24, (2) p. 189.
- 1925 Rustless steel V2A and its use in apparatus construction,
B. Strausz, - Apparatebau 37, 309, 321.
- 1925 Non-corrodible steels,
Iron Age 116, p. 515; Foundry Trade Journal 32, p. 120.

- 1925 The possibilities of stainless and similar corrosion resisting steels in the chemical and allied industries,
W. H. Hatfield, - Ind. Chem. 1, 64.
- 1925 Bibliography of stainless steel and stainless iron,
V. S. Polansky, - Carnegie Library, Pittsburgh.
- 1925 Rust-resisting metals - Chap. XX,
F. M. Becket, Chemistry in Industry 2, p. 346,
Chemical Foundation, N. Y.
- 1925 Non-corrosive steels,
Tech. Engng. News 6, 102, 124, 126.
- 1925 Corrosion of non-rusting iron and steel alloys at different temperatures,
A. Brunner, - Mech. Eng. 47, p. 749.
- 1925 Modern developments in steels resistant to corrosion,
W. H. Hatfield, Eng. 120, Nov. 20, p. 657;
Engng. 120, p. 657.
- 1925 Recent developments in corrosion resisting steels,
W. H. Hatfield, - Engng. 119, Mar. 13, p. 319;
Apr. 17, p. 431.
- 1925 Recent developments in stainless steel,
D. G. Clark, - Am. Iron and Steel Inst. Year-book, p. 289.
- 1926 Progress in the chromium and chromium-nickel corrosion-resisting steels in industry,
W. H. Hatfield, - Ind. Chemist, 2, 11, 1.
- 1926 Non-corrodible nickel-chromium steels,
Metallurgist, Feb. 26, p. 25.

Nickel and Other Alloy Steels.
 (See Chromium Steels)

- 1914 How molybdenum steel corrodes,
 Iron Trade Rev. 54, p. 834.
- 1922 Corrosion as affecting the metals used in the mechanical arts,
 W. H. Hatfield, - Engineer, 134, p. 639.
 (deals with 30% Ni steel and nichrome)
- 1923 Influence of nickel and chromium upon the solubility of steel (in relation to corrosion),
 W. H. Hatfield, - Iron and Steel Inst. 108, (2)
 p. 103.
- 1923 Invar and related nickel steels,
 Bureau of Standards Circular 58, Superintendent of Documents, Government Printing Office, 30¢
- 1923 Characteristics of some manganese steels,
 (corrosion-resistance of austenitic nickel-manganese steel).
 J. Strauss, - Trans. A. S. S. T. IV, p. 707.
- 1924 Nickel and its alloys,
 Bureau of Standards Circular 100, Superintendent of Documents, Government Printing Office, 40¢
 p. 162

Silicon Irons and Steels

- 1913 The influence of silicon on the corrosion of cast iron,
J. N. Friend, C. W. Marshall, - Iron and Steel
Inst. 88 (1) p. 382; Foundry 41, p. 307.
- 1921 By fusing iron with its silicide a metal is made
resisting corrosion and erosion,
Coal Age, 20, p. 924.
- 1922 Duraloy, a new heat-resisting metal,
Auto. Ind. 47, p. 1165.
- 1923 Handling corrosive solutions,
Paper, 31, p. 110
- 1923 Acid-Resisting Irons - P. D. Schenck, Chem. Met.
Eng. 25, p. 678.
- 1923 Acid resisting metal unique; castings made of
high-silicon iron melted and remelted in an air
furnace with the addition of 50% ferrosilicon,
H. E. Diller, - Foundry 51, p. 47.
- 1924 Duriron; its real worth not wholly appreciated
yet, - Brass World 20, p. 21.
- 1924 Corrosion-resistant, heat-resistant and electrical
resistance alloys,
Symposium A. S. T. M. 24 (2) p. 189.
- 1924 Rustless cast iron,
Bull. British Cast Iron Research Assn. Vol. 1,
June, p. 275.

Corrosion of Zinc-Coated Irons and Steels.

- 1899 Action of water on zinc and galvanized iron,
H. E. Davies, - Jour. Soc. Chem. Ind. 18, p. 102.
- 1905 Investigation of the properties of zinc coatings,
C. F. Burgess, Electrochem. Met. Ind. 3, 17.
- 1905 Comparison tests on galvanized iron and steel goods
coated by the hot and electrolytic methods,
I. Szirmay, - Z. Elektrochem., 11, p. 335;
Jour. Soc. Chem. Ind. 24, p. 679.
- 1905 Test of the security from rust of galvanized iron
and steel wires, and galvanized iron and steel barb-
ed wire,
I. Szirmay, - Z. F. Electrochem. 11, p. 333.
- 1912 Corrosion of zinc coated iron pipes,
Mitt. Kgl. Materialprüfungsamt 30 p. 101; Jour.
Soc. Chem. Ind. 31, p. 589.
- 1912 Corrosion tests with galvanized iron pipes,
E. Heyn, O. Bauer, - Mitt. aus dem Königl. che
Material 30, p. 101.
- 1912 Über die Verwendung von Verzinkten Eisenrohren und
Zink Rohren als Ersatz für Bleirohre bei Hauswasser-
leitung.
O. Kroehnke, J. F. Gasbeleuchtung und Wasser-
versorgung 56, 421.
- 1912 Angriffsversuche mit Verzinkten Eisenrohren,
E. Heyn, O. Bauer, Mitt. Königl. chen Mater-
ialprüfungsamt 30, p. 101.
- 1913 Corrosion and rusting experiments with sherardized
wrought iron,
F. Halla, - Z. Elektrochem, 19, p. 221.
- 1916 Galvanized iron roofing in the Philippines,
A. S. Argeulles, - Philippine Journal Sci.
11 p. 177.
- 1919 Resistance of galvanized sheet metal to rust,
M. Schlotter, - Stahl u. Eisen 39 (1.) p. 243.
- 1919 Corrosion tests of galvanized sheets,
M. Schlotter, - Stahl u. Eisen 39, p. 243;
Iron and Steel Inst. p. 534.

- 1920 Galvanized culverts,
L. G. Carnick, - Public Roads, U. S. Dept. of
Agri. 3, p. 26; Can. Eng. 39, p. 223; Jour. Inst.
Met. 28, p. 539.
- 1920 Testing of galvanized culverts for serviceability,
L. G. Carnick, - Can. Eng. 39, p. 223.
- 1921 Corrugated metal culverts,
J. L. G. Strad. - Canad. Eng. 40, p. 170.
- 1921 Influence of ferrous base metals on galvanized
coatings,
D. M. Strickland, - Raw Material 4, p. 443.
- 1922 Protective metallic coatings for the rustproofing
of iron and steel,
Bureau of Standards Circular 80, Superintendent
of Documents, Government Printing Office, 20¢
- 1924 Corrosion resistance of steel electroplated with
zinc and with zinc-mercury alloy,
C. J. Werulund, - Trans. Am. Electrochem. Soc.
45.
- 1925 Galvanized second sheets (thickness of coating and
gage of base) Editorial,
Iron Age 115, p. 1517.
- 1925 Comparative corrosion tests of hot galvanized sheet
iron and sheets galvanized by spraying,
C. Hoerhaus, - Zeit. & Met. 17, p. 69.
- 1925 The influence of impurities in zinc on its solu-
bility in acids,
R. Vondracek, -J. Izakkrizko, - Rec. Trav.
Chim. 44, p. 376; Chem. Abstract 19, p. 2899.

- 1925 Zinc and the problem of corrosion,
A. Billaz, L'industrie Chim. May, Oct, Dec;
Make it of zinc, 8, p. 3.
- 1925 Corrosion in the refrigerating industry,
Report of the corrosion committee,
Refrigerating Engineering 12, pp. 158-65,
Nov. 1925.
- 1925 Action of calcium chloride brines on galvanized
coatings,
A. O. White, Ind. Eng. Chem. 17, p. 503.

Non-ferrous Alloys.

See national Research Council bibliographies, chemical abstracts, Jour. British Inst. Metals, Trans. American Inst. Mining and Met. Engrs. and Proceedings, American Society for Testing Materials.



